

Technical data

90g/m² - 2 sides coated

GRIP SHEET®

| TEST | UNIT | NORM | VALUE | SPECIFICATIONS |
|------------------------|------------------|---------------------|-------|----------------|
| ■ Weight final product | g/m ² | NF EN ISO 536, 1996 | 123 | |
| ■ Thickness | µm | NF EN ISO 534, 2005 | 229 | 216 - 241 |

BREAKING STRENGTH IN TENSION

| | | | | |
|------------------------|--------------------------------------|------------------------|----|------|
| ■ Resistance | kN/m | NF EN ISO 1924.2, 1995 | SM | 5,88 |
| | | | ST | 1,94 |
| ■ Rupture length | meters | | SM | 4955 |
| | | | ST | 1635 |
| ■ Elongation | % | | SM | 1,6 |
| | | | ST | 2,2 |
| ■ Burst Index | kPa | NF EN ISO 2758, 2004 | | 190 |
| ■ Friction coefficient | ° | NF Q 03-083,1993 | SM | 52,6 |
| ■ air porosity | cm ³ /m ² .Pas | NF ISO 5636.3, 1992 | | 6,6 |
| ■ toxicity | | | | None |
| ■ Skin irritation | | | | None |
| ■ Reuse | | NF EN 13429 | | Yes |
| ■ Recyclability | | | | Yes |



- Pallet quantity = 5,000 sheets
- % of tolerance : 2%
- Warehousing conditions: Insensitive to heat/cold

